

**Crepe paper**

Crepe paper is made of insulating paper which is produced by 100% pure pulp imported and processed by special wrinkling process. With good oil-soluble performance it is widely used in oil-immersed transformers, transformers, power reactors around the package parts of the insulation, the insulation package by the lead parts. Crepe paper improved the electrical and mechanical properties of the insulation structure.

**产品规格 Thickness:**

规格 Thickness	
厚度	0.05mm、0.08mm、 0.10mm、 0.13mm、 0.20mm
宽度	25mm、 30mm、 40mm~960mm

**Storage**

Product should be stored in dry and clean interior. It should not be near the fire source, heat source or direct sunlight

**皱纹纸性能指标 Items**

序号 No	性能 Items		单位 Unit	要求 Requirement
1	厚度公差 Thickness tolerance		mm	±0.05
2	皱纹数 number of wrinkles		个/10mm	代号要求中数值 Code requirements
3	定量公差 Quantitative tolerances		%	代号要求数值的±10 Code requirements±10
4	断裂伸长率 Elongation at Break		%	代号要求数值的±15 Code requirements±10
5	吸油高度 Oil absorption height	纵向 MD	mm/10min	≥7
			mm/60min	≥30
		横向 CMD	mm/10min	≥20
			mm/60min	≥50
6	水分 Moisture		%	≤8
7	灰分 Ash Content		%	≤1
8	水抽出物电导率 Conductivity of A0queous Extract		mS/m	≤10
9	水抽出物 PH PH of A0queous Extract		-	6~8
10	电气强度 (油中) Electric break down strength (in oil)		mV/m	≥20
11	对变压油的污染 Transformer oil pollution		-	tanδ<0.001